

Escorene™ Ultra LD 720 Series

Ethylene Vinyl Acetate Copolymer Resin

Product Description

Escorene™ Ultra LD 720 resins are high vinyl acetate copolymer specialty film resins designed for applications requiring outstanding heat sealability, along with excellent strength properties and toughness. These resins are also used in specialized molding applications.

General

Availability ¹	<ul style="list-style-type: none"> ▪ Asia Pacific ▪ Latin America ▪ North America
Additive	<ul style="list-style-type: none"> ▪ LD 720.62: Antiblock: No; Slip: No; Thermal Stabilizer: Yes ▪ LD 720.AW: Antiblock: 10000 ppm; Slip: 7050 ppm; Thermal Stabilizer: Yes ▪ LD 720.NM: Antiblock: No; Slip: No; Thermal Stabilizer: Yes ▪ LD 720.01: Antiblock: 10000 ppm; Slip: 7050 ppm; Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> ▪ Heat Seal Layer ▪ Injection Molding ▪ Shoe Soles
Revision Date	<ul style="list-style-type: none"> ▪ 11/29/2018

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.947 g/cm ³	0.947 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	1.6 g/10 min	1.6 g/10 min	ASTM D1238
Vinyl Acetate Content	18.5 wt%	18.5 wt%	ExxonMobil Method
Peak Melting Temperature	187 °F	86 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	144 °F	62 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	3900 psi	27 MPa	ASTM D882
Tensile Strength at Break TD	4000 psi	28 MPa	ASTM D882
Elongation at Break MD	210 %	210 %	ASTM D882
Elongation at Break TD	640 %	640 %	ASTM D882
Secant Modulus MD - 1% Secant	8900 psi	61 MPa	ASTM D882
Secant Modulus TD - 1% Secant	9800 psi	68 MPa	ASTM D882
Dart Drop Impact	400 g	400 g	ASTM D1709A
Elmendorf Tear Strength MD	50 g	50 g	ASTM D1922
Elmendorf Tear Strength TD	80 g	80 g	ASTM D1922
Puncture Force	6 lbf	25 N	ExxonMobil Method
Puncture Energy	6.0 in·lb	0.68 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	43	43	ASTM D2457
Haze	> 30 %	> 30 %	ASTM D1003

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

Film (1.5 mil / 38 micron) made from LD 720.01 on a 2.5 inch blown film line with a 6 inch die and 30 mil die gap at a 2.5:1 blow-up ratio and melt temperature of 320-340°F (160-171°C).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra LD 720 Series
Ethylene Vinyl Acetate Copolymer Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com