

ExxonMobil™ HDPE HD 6601.29

High Density Polyethylene Copolymer Resin

Product Description

HD 6601 is a narrow molecular weight hexene copolymer designed for a wide range of injection molding applications, offering excellent ESCR with good stiffness-toughness balance. Ideally suited for articles requiring rugged physical performance in cold temperature environments.

General

| | |
|---------------------------|---|
| Availability ¹ | <ul style="list-style-type: none"> Latin America North America |
| Additive | <ul style="list-style-type: none"> Long Term UV-15 Stabilizer: Yes |
| Applications | <ul style="list-style-type: none"> Automotive Components Industrial Components Industrial Closures Recreational Vehicle - Components Waste Carts |
| Revision Date | <ul style="list-style-type: none"> 03/13/2015 |

| Resin Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|-------------------------|------------------|
| Density | 0.948 g/cm ³ | 0.948 g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 5.0 g/10 min | 5.0 g/10 min | ASTM D1238 (mod) |

| Thermal | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|--------------------|---------------|
| Deflection Temperature Under Load (DTUL) at 66psi - Unannealed | 156 °F | 69 °C | ASTM D648 |
| Deflection Temperature Under Load (DTUL) at 264psi - Unannealed | 108 °F | 42 °C | ASTM D648B |
| Peak Melting Temperature | 266 °F | 130 °C | ASTM D3418 |

| Molded Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|---------------------------------------|-------------------------|--------------------|-------------------|
| Tensile Strength at Yield | 3400 psi | 23 MPa | ASTM D638 |
| Elongation at Break | 1000 % | 1000 % | ExxonMobil Method |
| Flexural Modulus | | | ASTM D790B |
| 1% Secant | 160000 psi | 1100 MPa | |
| 2% Secant | 140000 psi | 970 MPa | |
| Environmental Stress-Crack Resistance | | | ASTM D1693B |
| 10% Igepal, F50 | 20 hr | 20 hr | |

| Impact | Typical Value (English) | Typical Value (SI) | Test Based On |
|-------------------------------------|-------------------------|--------------------|---------------|
| Notched Izod Impact (-40°F (-40°C)) | 1.0 ft-lb/in | 55 J/m | ASTM D256 |

Additional Information

- Properties are based on compression molded samples.
- Test procedures may be modified to accommodate operating conditions or facility limitations.
- Tensile Strength at Yield and Elongation at Break tested using ASTM D638 Type IV, 50 mm/min.

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ HDPE HD 6601.29
High Density Polyethylene Copolymer Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com