

Escorene™ Ultra FL 00212

Ethylene Vinyl Acetate Copolymer Resin

Product Description

FL 00212 is a copolymer of ethylene and vinyl acetate. Processing Conditions Processing temperatures above 260 °C (500 °F) may cause resin degradation. Machines should always be purged with LDPE or a suitable cleaning compound before shutdown.

General

Availability ¹	▪ Africa & Middle East	▪ Asia Pacific	▪ Europe
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Cast Film ▪ Co-Extrusion Films	▪ Compounding ▪ Freezer Film	▪ Injection Molding ▪ Stretch Film
Revision Date	▪ 01/01/2017		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.934 g/cm ³	0.934 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	2.5 g/10 min	2.5 g/10 min	ASTM D1238
Vinyl Acetate Content	12.0 wt%	12.0 wt%	ExxonMobil Method
Peak Melting Temperature	202 °F	94 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	159 °F	71 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus (0.20 in/min (5.0 mm/min))	12000 psi	85 MPa	ASTM D638
Elongation at Break (20 in/min (500 mm/min))	> 100 %	> 100 %	ASTM D638
Durometer Hardness (Shore A, 15 sec)	94	94	ASTM D2240

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	4400 psi	30 MPa	ASTM D882
Tensile Strength at Break TD	4000 psi	28 MPa	ASTM D882
Elongation at Break MD	530 %	530 %	ASTM D882
Elongation at Break TD	660 %	660 %	ASTM D882
Secant Modulus MD - 1% Secant	11000 psi	78 MPa	ASTM D882
Secant Modulus TD - 1% Secant	12000 psi	83 MPa	ASTM D882
Dart Drop Impact	480 g	480 g	ASTM D1709A
Elmendorf Tear Strength MD	110 g	110 g	ASTM D1922
Elmendorf Tear Strength TD	160 g	160 g	ASTM D1922

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film properties were measured on a 50µm (1.97 mil) thick film extruded on a conventional LDPE extruder (screw diameter 60mm (2.36 in), rotating die diameter : 200mm (7.87 in), die gap : 1 mm (39.4mil), BUR 2.5:1, die temperature 180°C (356°F)). Molded properties were measured on 2 mm (78.7 mil) thick compression molded plaques prepared based on ASTM D 4703 Procedure C (tensile ASTM D 638 : Type IV dumbbell, hardness ASTM D 2240 : 3 plied up disks).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra FL 00212
Ethylene Vinyl Acetate Copolymer Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com