

# Escorene™ Ultra UL 00114

## Ethylene Vinyl Acetate Copolymer Resin

### Product Description

UL00114 is a fractional MI copolymer of ethylene and vinyl acetate.

### General

Availability <sup>1</sup>	▪ Africa & Middle East	▪ Asia Pacific	▪ Europe
Additive	▪ UL 00114: Antiblock: No; Slip: No; Thermal Stabilizer: No; Free Flowing Agent: No		
Applications	▪ Compounding	▪ Halogen-free flame retardant (HFFR) compounds	▪ Wire and Cable Compounds
Revision Date	▪ 04/01/2019		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.936 g/cm <sup>3</sup>	0.936 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	0.73 g/10 min	0.73 g/10 min	ASTM D1238
Vinyl Acetate Content	14.0 wt%	14.0 wt%	ExxonMobil Method
Peak Melting Temperature	196 °F	91 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	159 °F	71 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus (0.20 in/min (5.0 mm/min))	9800 psi	68 MPa	ASTM D638
Tensile Strength at Break			ASTM D638
20 in/min (500 mm/min)	2400 psi	16 MPa	
Elongation at Break (20 in/min (500 mm/min))	780 %	780 %	ASTM D638
Durometer Hardness			ASTM D2240
Shore A, 15 sec	94	94	
Shore D, 15 sec	38	38	

Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Volume Resistivity (500 V)	1.1E+15 ohms·m	1.1E+15 ohms·m	IEC 62631-3-1
Relative Permittivity (50 Hz)	2.73	2.73	IEC 62631-2-1
Dissipation Factor (50 Hz)	2.8E-3	2.8E-3	IEC 62631-2-1

### Legal Statement

This product is not intended for use in food contact application.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

### Processing Statement

Molded properties were measured on 2 mm (78.7 mil) thick compression molded plaques prepared based on ASTM D 4703 Procedure C (Tensile ASTM D 638 : Type IV dumbbell).

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra UL 00114  
Ethylene Vinyl Acetate Copolymer Resin

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)