Ex on Mobil

Exxtral[™] Performance Polyolefin CMU201 Polypropylene, Compounded (TPO)

Product Description

A specialty thermoplastic polyolefin resin designed for automotive interior covered applications such as retainers in which a good stiffness toughness balance is required.

General					
Availability ¹	Africa & Middle East	• Europe			
Features •	Creep Resistant	Good Dimensional Stability Low Warpage			
Uses •	Automotive Applications	Automotive Interior Trim			
	Automotive Interior Parts	 Automotive Under the Hood 			
Appearance •	Black				
Form(s)	Pellets				
Processing Method •	Injection Molding				
Revision Date	06/28/2021				
Physical	Typical Value (English)	Typical Value (SI)	Test Based On		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) 15 a/10 min	15 a/10	min ISO 1133		

15	(10 :			
13	g/10 min	15	g/10 min	ISO 1133
17	cm ³ /10min	17	cm ³ /10min	ISO 1133
1.05	g/cm³	1.05	g/cm³	ISO 1183
Typical Value	(English)	Typical Value	(SI)	Test Based On
3630	psi	25.0	MPa	ISO 527-2/50
3.0	%	3.0	%	ISO 527-2/50
336000	psi	2320	MPa	ISO 527-1
339000	psi	2340	MPa	ISO 178
Typical Value	(English)	Typical Value	(SI)	Test Based On
2.6	ft·lb/in²	5.5	kJ/m²	ISO 179
T !) /		The fact by failing		Test Deserved On
	-	71		Test Based On ISO 75-2/A
	1.05 Typical Value 3630 336000 336000 339000 Typical Value 2.6 Typical Value	17 cm³/10min 1.05 g/cm³ Typical Value (English) 3630 psi 336000 psi 339000 psi Typical Value (English) 2.6 ft·lb/in² Typical Value (English) 140 °F	1.05 g/cm³1.05Typical Value (English)Typical Value3630 psi25.03.0 %3.0336000 psi2320339000 psi2340Typical Value (English)Typical Value2.6 ft·lb/in²5.5Typical Value (English)Typical Value	1.05g/cm³Typical Value(English)Typical Value(SI)3630psi25.0MPa3.0%3.0%336000psi2320MPa339000psi2340MPaTypical Value(English)Typical Value(SI)2.6ft·lb/in²5.5kJ/m²Typical Value(English)Typical Value(SI)2.6ft·lb/in²5.5kJ/m²

Legal Statement

This product is not intended for use in food contact application.

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Exxtral™ Performance Polyolefin CMU201

Polypropylene, Compounded (TPO)

E‰onMobil

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com