

ExxonMobil™ LLDPE LL 6100.17

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LL 6100.17 is a narrow molecular weight butene copolymer designed for applications that require easy processability. This resin offers outstanding toughness and tear resistance in freezer applications for food packaging.

General						
Availability ¹	 Latin America 		 North America 			
Additive	Antiblock: No		Slip: No		Thermal Stabilizer: Yes	
Applications	 Closures and Dispensers 		 Housewares 		 Protective Caps 	
Form(s)	 Pellets 					
Revision Date	• 06/11/2020					
Resin Properties	Typical Value	(English)	Ту	pical Value	(SI)	Test Based On
Density	0.925	g/cm³		0.925	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	20	g/10 min		20	g/10 min	ASTM D1238
Peak Melting Temperature	250	°F		121	°C	ExxonMobil Method
Thermal	Typical Value	(English)	Ту	pical Value	(SI)	Test Based On
Vicat Softening Temperature	189	°F		87.0	°C	ExxonMobil Method
Molded Properties	Typical Value	(English)	Ту	pical Value	(SI)	Test Based On
Tensile Strength at Yield	1900	_	·	13	MPa	ExxonMobil Method
Elongation at Break	360	%		360	%	ExxonMobil Method
Flexural Modulus						ExxonMobil
1% Secant : Procedure B	69000	psi		480	MPa	Method
2% Secant : Procedure B	60000	psi		410	MPa	
Environmental Stress-Crack Resistance Condition B, 10% Igepal, F50	110	hr		110	hr	ExxonMobil Method

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Effective Date: 06/11/2020 ExxonMobil Page: 1 of 2



ExxonMobil™ LLDPE LL 6100.17 Linear Low Density Polyethylene Resir

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com