ExxonMobil

Paxon™ BA53-055

High Density Polyethylene Resin

Product Description

Paxon™ BA53-055 is a high molecular weight, high-density polyethylene copolymer. This resin has superior stress crack resistance, high impact strength and good rigidity.

General

Availability [1]	▪ Latin America	▪ North America	
Additive	▪ Antistatic: No		
Applications	▪ Drums ▪ Food Packaging	▪ Heavy Gauge Sheet ▪ Large Part Blow Molding	▪ Thermoformed Parts
Form(s)	▪ Pellets		
Revision Date	▪ 08/21/2020		

Resin Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Density	0.954	g/cm³	0.954	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	< 0.10	g/10 min	< 0.10	g/10 min	ASTM D1238
High Load Melt Index (190°C/21.6 kg)	5.3	g/10 min	5.3	g/10 min	ASTM D1238

Thermal	Typical Value (English)		Typical Value (SI)		Test Based On
Vicat Softening Temperature	261	°F	127	°C	ASTM D1525
Peak Melting Temperature	270	°F	132	°C	ExxonMobil Method
Crystallization Peak, Tc	243	°F	117	°C	ExxonMobil Method

Molded Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Tensile Strength at Yield	4000	psi	28	MPa	ASTM D638
Flexural Modulus					
1% Secant : 0.051 in/min (1.3 mm/min)	150000	psi	1000	MPa	ASTM D790A
2% Secant	120000	psi	860	MPa	ASTM D790
Environmental Stress-Crack Resistance					ASTM D1693B
100% Igepal	> 1000	hr	> 1000	hr	
Durometer Hardness (Shore D, 15 sec)	62		62		ASTM D2240

Impact	Typical Value (English)		Typical Value (SI)		Test Based On
Charpy Notched Impact Strength					ISO 179/1eA
-4°F (-20°C)	9.5	ft·lb/in²	20	kJ/m²	
73°F (23°C)	13	ft·lb/in²	27	kJ/m²	

Additional Information

All molded properties were measured on compression molded plaques. BA53-055 has UL recognition. Contact your ExxonMobil Chemical representative for details.

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil

Paxon™ BA53-055
High Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com