

ExxonMobil™ HDPE HD 6714.17

High Density Polyethylene Resin

Product Description

HD 6714 is a narrow molecular weight hexene copolymer designed for a wide range of injection molding applications requiring easy processability and good toughness properties. This resin is ideally suited for articles requiring low warpage, glossy surfaces and good cold temperature impact performance.

General

Availability ¹	▪ Latin America	▪ North America
Additive	▪ Antioxidant	
Applications	▪ Bins ▪ Closures and Dispensers	▪ Food Packaging Containers ▪ Protective Caps ▪ Housewares
Revision Date	▪ 06/22/2015	

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.952 g/cm ³	0.952 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	14 g/10 min	14 g/10 min	ASTM D1238

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	160 °F	71 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	113 °F	45 °C	ASTM D648
Peak Melting Temperature	264 °F	129 °C	ASTM D3418

Molded Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (50 mm/min)	3600 psi	25 MPa	ASTM D638
Elongation at Break	250 %	250 %	ExxonMobil Method
Flexural Modulus 1% Secant 2% Secant	180000 psi 160000 psi	1200 MPa 1100 MPa	ASTM D790
Environmental Stress-Crack Resistance 10% Igepal, F50	3 hr	3 hr	ASTM D1693B

Impact

	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (-40°F (-40°C))	0.77 ft-lb/in	41 J/m	ASTM D256

Additional Information

- Properties are based on compression molded samples.
- Test procedures may be modified to accommodate operating conditions or facility limitations.
- Tensile Strength at Yield and Elongation at Break tested using ASTM D638 Type IV, 50 mm/min.

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ HDPE HD 6714.17
High Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com