

# Exact™ 3131A

## Ethylene-based Plastomer Resin

### Product Description

Exact™ 3131A is an ethylene-based hexene plastomer produced using ExxonMobil Chemical's EXXPOL® Catalyst Technology. Exact™ 3131A is designed for both monolayer and multilayer coextruded cast film applications requiring excellent toughness and heat sealing performance. TnPP is not intentionally added to Exact™ 3131A resin.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Latin America</li> <li>North America</li> </ul>
Additive	<ul style="list-style-type: none"> <li>Antiblock: No</li> <li>Slip: No</li> <li>Thermal Stabilizer: Yes</li> </ul>
Applications	<ul style="list-style-type: none"> <li>Cast Film</li> <li>Food Packaging Heat Seal Layers</li> <li>Industrial Packaging</li> </ul>
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>10/23/2019</li> </ul>

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.900 g/cm <sup>3</sup>	0.900 g/cm <sup>3</sup>	ASTM D1505
Melt Index <sup>2</sup> (190°C/2.16 kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238
Peak Melting Temperature	203 °F	95 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	181 °F	82.6 °C	ExxonMobil Method
Crystallization Peak, T <sub>c</sub>	171 °F	77 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	780 psi	5.4 MPa	ASTM D882
Tensile Strength at Yield TD	550 psi	3.8 MPa	ASTM D882
Tensile Strength at Break MD	9800 psi	70 MPa	ASTM D882
Tensile Strength at Break TD	7800 psi	50 MPa	ASTM D882
Elongation at Break MD	440 %	440 %	ASTM D882
Elongation at Break TD	650 %	650 %	ASTM D882
Secant Modulus MD	8800 psi	61 MPa	ASTM D882
Secant Modulus TD	10000 psi	70 MPa	ASTM D882
Dart Drop Impact	790 g	790 g	ASTM D1709A
Elmendorf Tear Strength MD	210 g	210 g	ASTM D1922
Elmendorf Tear Strength TD	480 g	480 g	ASTM D1922
Puncture Force	14 lbf	61 N	ExxonMobil Method
Puncture Energy	47 in-lb	5.3 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	92	92	ASTM D2457
Haze	0.5 %	0.5 %	ASTM D1003

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

**Exact™ 3131A**  
Ethylene-based Plastomer Resin**Processing Statement**

Film (1 mil / 25.4 micron) made on a 3.5 inch cast film line with a 5 inch melt curtain, 80°F (27°C) chill roll temperature at a 500 ft/min take-off speed and a melt temperature between 470-530°F (243-277°C).

**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Value reported is an estimate based on ExxonMobil's correlation from melt flow rate data measured at other standard conditions, based on ASTM D 1238.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)