

ExxonMobil™ LLDPE LL 1201BS

Linear Low Density Polyethylene Resin

Product Description

LL 1201BS is a LLDPE grade, offering excellent combination of stiffness and optical properties (when blended with 10-20% LDPE). TnPP is not intentionally added to LL 1201BS.

General

Availability ¹	▪ Europe
Additive	▪ LL 1201BS: Antiblock: 750 ppm; Slip: 1250 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> ▪ Blown Film ▪ Bread Bags ▪ Food Packaging ▪ Form Fill And Seal Packaging ▪ Garment Film ▪ General Packaging ▪ Industrial Packaging ▪ Label Film ▪ Lamination Film ▪ Multilayer Packaging Film ▪ Overwrap Film ▪ Packaging Films ▪ Produce Bags ▪ Shoppers ▪ Shrink Film ▪ Stand Up Pouches ▪ Trash Bags ▪ Zipper Bag
Revision Date	▪ 05/22/2018

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.925 g/cm ³	0.925 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.70 g/10 min	0.70 g/10 min	ASTM D1238
Peak Melting Temperature	253 °F	123 °C	ExxonMobil Method

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	8700 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	6100 psi	42 MPa	ASTM D882
Elongation at Break MD	620 %	620 %	ASTM D882
Elongation at Break TD	910 %	910 %	ASTM D882
Secant Modulus MD - 1% Secant	44000 psi	300 MPa	ASTM D882
Secant Modulus TD - 1% Secant	48000 psi	330 MPa	ASTM D882
Dart Drop Impact	70 g	70 g	ASTM D1709A
Elmendorf Tear Strength MD	50 g	50 g	ASTM D1922
Elmendorf Tear Strength TD	450 g	450 g	ASTM D1922

Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	53	53	ASTM D2457
Haze	12 %	12 %	ASTM D1003

Legal Statement

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

The film properties have been measured on a 30 µm (1.18 mil) thick film. (Blow-up ratio : 2.5)

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LLDPE LL 1201BS
Linear Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2021 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com