

Paxon™ BZ45-060

High Density Polyethylene Resin

Product Description

Paxon™ BZ45-060 is a high molecular weight high density polyethylene copolymer which contains an UV inhibitor. It provides a combination of excellent processability, outstanding melt strength, high impact strength, chemical resistance and high stress cracking resistance.

General

Availability ¹	- Africa & Middle East - Europe	- Latin America - North America
Additive	UV Stabilizer	
Applications	Intermediate Bulk Containers	
Revision Date	06/03/2020	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.946 g/cm ³	0.946 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	< 0.10 g/10 min	< 0.10 g/10 min	ASTM D1238
High Load Melt Index (190°C/21.6 kg)	6.3 g/10 min	6.3 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	148 °F	65 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	3500 psi	24 MPa	ExxonMobil Method
Flexural Modulus - 1% Secant (0.050 in/min (1.3 mm/min))	120000 psi	820 MPa	ExxonMobil Method
Environmental Stress-Crack Resistance 100% Igepal	> 1000 hr	> 1000 hr	ExxonMobil Method
Durometer Hardness (Shore D, 15 sec)	53	53	ExxonMobil Method

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Charpy Notched Impact Strength -4°F (-20°C), Type 1, Edgewise, Notch A	8.9 ft-lb/in ²	19 kJ/m ²	ExxonMobil Method
73°F (23°C), Type 1, Edgewise, Notch A	12 ft-lb/in ²	25 kJ/m ²	

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

This product is not intended for use in fuel systems utilizing biodiesel.

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Paxon™ BZ45-060
High Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com