

Exxon™ Butyl 365S

Rubber

Product Description

Exxon™ Butyl 365S is a copolymer of isobutylene and isoprene. Exxon™ Butyl Rubber is a trademark designating a series of polymers made by copolymerizing isobutylene with small amounts of isoprene.

Key Features

Exxon™ butyl 365S is nonpolar, relatively inert chemically, and is known for its excellent resistance to aging and very low permeability to gases. The grade 365S is a low viscosity, high unsaturation grade used primarily for cable insulation, mechanical goods, and capacitor sealing and blend component with high viscosity butyl polymers for improving processability.

General

Availability ¹	- Africa & Middle East - Asia Pacific	- Europe - Latin America	North America
Appearance	Uniform, white to light amber in color; free of contamination		
Form(s)	Bale		
Revision Date	02/06/2023		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.91 g/cm ³	0.91 g/cm ³	ASTM D297
Mooney Viscosity ² (ML 1+8, 257°F (125°C))	33 MU	33 MU	ASTM D1646 (mod)
Antioxidant (non-staining)	0.03 wt% min	0.03 wt% min	ExxonMobil Method
Water	0.3 wt% max	0.3 wt% max	ExxonMobil Method
Volatiles	< 0.6 wt%	< 0.6 wt%	ASTM D5668 (mod)
Unsaturation	2.30 mol%	2.30 mol%	ExxonMobil Method
Ash	< 0.4 wt%	< 0.4 wt%	ASTM D5667 (mod)

Additional Information

Storage: All inventory must be stored in dry conditions in an enclosed warehouse, protected from contaminants, and outdoor light exposure (including during shipment and transfers). Shipping Policy: ExxonMobil's policy is to not ship products over 3 years old from the date of production. Packaging: 34+/-0.68kg bales in dispersible EVA film or release film. For material with dispersible film wrap, Vicat softening point less than or equal to 85°C (ASTM 1525-87). Pallets of 36 bales (1224kgs).

Legal Statement

For detailed product compliance information, please contact customer Service.

This product is not intended for use in food contact applications.

This product, including the product name, shall not be used or tested in any medical application without prior written acknowledgement of ExxonMobil Chemical as to the intended use.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² MV 2000 or equivalent

Exxon™ Butyl 365S
Rubber

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com