

# ExxonMobil™ PP7032KN

## Polypropylene Impact Copolymer

### Product Description

A high crystallinity, excellent stiffness, high impact copolymer resin designed for injection molding, extrusion and thermoforming applications.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>Europe</li> <li>Latin America</li> </ul>	<ul style="list-style-type: none"> <li>North America</li> </ul>
Features	<ul style="list-style-type: none"> <li>Antistatic</li> <li>Balanced Stiffness/Toughness</li> </ul>	<ul style="list-style-type: none"> <li>Medium Flow</li> <li>Nucleated</li> </ul>	<ul style="list-style-type: none"> <li>Ultra High Impact Resistance</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Consumer Applications</li> <li>Crates</li> </ul>	<ul style="list-style-type: none"> <li>Industrial Applications</li> <li>Pallets</li> </ul>	<ul style="list-style-type: none"> <li>Tool/Tote Box</li> <li>Toys</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Natural Color</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>		
Revision Date	<ul style="list-style-type: none"> <li>10/09/2019</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Density	0.900 g/cm <sup>3</sup>	0.900 g/cm <sup>3</sup>	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	3660 psi	25.2 MPa	ASTM D638
Tensile Stress at Yield	3570 psi	24.6 MPa	ISO 527-2/50
Elongation at Yield (2.0 in/min (51 mm/min))	5.3 %	5.3 %	ASTM D638
Tensile Strain at Yield	4.7 %	4.7 %	ISO 527-2/50
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	201000 psi	1380 MPa	ASTM D790A
0.51 in/min (13 mm/min)	219000 psi	1510 MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	198000 psi	1360 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact 0°F (-18°C)	1.5 ft-lb/in	80 J/m	ASTM D256A
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength -40°F (-40°C)	3.7 ft-lb/in <sup>2</sup>	7.7 kJ/m <sup>2</sup>	ISO 180/1A
0°F (-18°C)	4.4 ft-lb/in <sup>2</sup>	9.2 kJ/m <sup>2</sup>	
73°F (23°C)	25 ft-lb/in <sup>2</sup>	52 kJ/m <sup>2</sup>	
Charpy Notched Impact Strength -4°F (-20°C)	3.7 ft-lb/in <sup>2</sup>	7.7 kJ/m <sup>2</sup>	ISO 179/1eA
73°F (23°C)	26 ft-lb/in <sup>2</sup>	55 kJ/m <sup>2</sup>	
Gardner Impact -20°F (-29°C), 0.125 in (3.18 mm), Geometry GC	231 in-lb	26.1 J	ASTM D5420

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa) Flatwise	125 °F	51.4 °C	ExxonMobil Method
Heat Deflection Temperature (0.45 MPa) Flatwise	204 °F	95.7 °C	ExxonMobil Method
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	223 °F	106 °C	ExxonMobil Method

ExxonMobil™ PP7032KN  
Polypropylene Impact Copolymer

#### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

#### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)