

Vistalon™ 3666B

Ethylene Propylene Diene Terpolymer Rubber

Product Description

Vistalon™ 3666B EPDM rubber is an oil extended terpolymer grade with a very high molecular weight, medium diene content, medium ethylene content and a broad molecular weight distribution. This product is sold in dense bale form.

Key Features

Major applications include TPVs, low hardness articles, appliance gaskets, shock absorbers, resilient profiles, and hoses with excellent compression set. This grade can be used in blends with other Vistalon EPDM grades to enhance elastic properties or filler loadability. Features include high elasticity and collapse resistance, as well as excellent low temperature properties.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Form(s)	<ul style="list-style-type: none"> Bale 		
Revision Date	<ul style="list-style-type: none"> 02/03/2025 		

Physical

	Typical Value (English)	Typical Value (SI)	Test Based On
Oil Content, Paraffinic	75 phr	75 phr	ExxonMobil Method
Mooney Viscosity ² (ML 1+4, 257°F (125°C))	50 MU	50 MU	ASTM D1646 (mod)
Ethylene Content ³	63.0 wt%	63.0 wt%	ASTM D3900A
Ethylidene Norbornene (ENB) Content	4.2 wt%	4.2 wt%	ASTM D3900A

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Radial cavity dies, polymer remassed at 145+/- 10°C.

³ Ethylene and VNB measured on reactor samples before oil injection. Product testing (if necessary) will use MEK extraction technique. Ethylene bias is 0.4 wt% and is subtracted from extracted product results, then compared to reactor spec of 59.0-65.0. No bias exists for VNB. Extracted product results are compared to reactors spec of 0.55-0.85.

For additional technical, sales and order assistance: [Contact Us](#)

©2026 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com